



SUPERIOR SUPERSAFE® No. 30DS



DOUBLE STRENGTH, VOC-FREE ORGANIC ACID FLUX

- Formulated for electronic, electrical, industrial, artisan, and aerospace applications, including:
 - ◆ Printed Circuit Boards (PCBs)
 - ◆ Wire, Cable, and Terminal Lead Tinning and Soldering
 - ◆ Flat and Round Wire Fabrication
 - ◆ Semiconductor and Component Lead Tinning
 - ◆ Stained Glass
- Used for Copper, Beryllium-Copper, Nickel, Alloy 42, Alloy 51, Brass, and some steels.
- VOC-Free formulation is non-hazardous and environmentally friendly.
- Conforms to IPC ANSI J-STD-004, Type ORM1.
- Broad activity range an excellent choice for Tin/Lead, Tin/Silver, Tin/Bismuth, and Indium solder alloys.

DESCRIPTION

Superior Supersafe® No. 30DS contains an amino acid-halide activator which starts to clean metals at room temperature, reaching peak fluxing activity at 260°C/500°F, where it promotes excellent solderability. The broad range of activity makes **Superior Supersafe® No. 30DS** an ideal choice for high production rates or difficult metal surface conditions where an active, but safe, flux is required.

APPLICATIONS

Superior Supersafe® No. 30DS can be used in dipping, spraying, brushing, swabbing, and many other fluxing operations. Soldering processes should include the following steps:

- ❶ Remove any oil, grease, mold release, or other contaminants from the surface to be soldered.
- ❷ Apply flux to joint by dipping, spraying, dragging, swabbing or brushing to area being soldered.
- ❸ Preheat or air-dry area to be soldered after flux has been applied to activate the flux and yield optimum soldering characteristics.
- ❹ Apply solder, dip part, or place iron to area being soldered.
- ❺ Clean flux residues from soldered area using de-ionized, distilled, RO, and in some cases tap water heated to a temperature of 60°C±5°C /140°F±10°F for best results. Room temperature water may also be used.

Post-solder residues from **Superior Supersafe® No. 30DS** are self-neutralizing at soldering temperatures, owing to the unique flux chemistry. However, removal of the residues is imperative for electronic applications to prevent corrosion to sensitive joints and components and promote long-term reliability of assemblies. The residues and raw flux are completely water soluble and should be washed in an aqueous cleaning system using de-ionized or distilled water heated to a recommended temperature of at least 60°C±5°C /140°F±10°F. The addition of one gram of non-ionic surfactant to four (4) liters of water is recommended to reduce the wash water surface tension and make it a more effective cleaner. Each user must determine the best cleaning procedure to meet required specifications.

Superior manufactures quality fluxes. Our business is solving problems.



It is recommended that flux be changed in soldering processes using a flux pot at least once a week to maintain consistent flux performance and provide maintenance and cleaning of the flux pot. However, different environmental conditions may necessitate more frequent or less frequent flux changes to be determined by the end-user.

Superior Supersafe® No. 30DS can be diluted in a 1:1 ratio of water to flux to yield the standard strength formulation of Superior No. 30. It is recommended that De-Ionized, Distilled, or Reverse Osmosis (RO) water be used to dilute the flux, however, tap water may be used.

CLASSIFICATIONS

- IPC ANSI-J-STD-004, Type ORM1
- Federal Specification O-F-506C, Type I, Form B.

PHYSICAL PROPERTIES

Form	Clear Blue Liquid
Specific Gravity	1.090 ± 0.01 @ 20-25°C/68-77°F
Density	9.1 Lbs / Gallon
pH	0.925 ± 0.225
Chloride Content	25 - 55 g chlorine/liter
Spread Factor	80 minimum
Surface Tension	35 dynes/cm maximum
Flash Point	None
Freezing Effect	None
Inorganic Cation Content	None
Recommended Soldering Range	95-315°C/200-600°F
Residues	Completely Water Soluble

THIS PRODUCT IS RoHS COMPLIANT

DISPOSAL

Superior No. 30DS is a VOC-Free flux containing organic activators. It has a water base that contains no alcohols, solvents, petroleum derivatives, or inorganic material additives

The following steps should be taken to effect proper disposal:

- ① Measure out the amount of flux for disposal.
- ② As a general rule, add soda ash in a 1 to 25 ratio of neutralizer to spent flux. This ratio may differ depending upon pre-neutralization solids content and/or pH.
- ③ When the neutralization bubbling subsides, the solution may be flushed down a drain. The neutralized solution has a pH of 6 to 8. Use a pH meter or paper to determine the pH.

Consult local, state, or federal EPA to determine local guidelines regarding disposal.

SAFETY PRECAUTIONS

Superior Supersafe® No. 30DS is a non-hazardous product, but should be treated as an industrial chemical. Store in plastic containers away from heat, sparks, or open flame. Do not store or place flux in contact with metals.

Adequate ventilation is necessary to remove flux fumes along with vapors and fumes from hot solder. Avoid breathing vapors and contact with skin, eyes and mucous membranes.

Refer to the MSDS for additional safety information.

discretion and risk. Since conditions of use are outside of Superior Flux & Mfg. Co.'s control, we cannot assume liability for results obtained or damage incurred due to misuse, nor can we assume customer liability.

Superior manufactures quality fluxes. Our business is solving problems.



**Superior Flux
& Mfg. Co.**

6615 Parkland Blvd. • Cleveland, OH 44139 • Phone: 440-349-3000 • Fax:
440-349-3003 www.superiorflux.com • e-mail: info@superiorflux.com