



SUPERIOR No. 420-S



VOC-FREE, NO-CLEAN FLUX

- VOC-Free, water-based formulation.
- Excellent wetting characteristics on HASL or OSP printed circuit boards (PCBs).
- No residue formulation eliminates post-solder cleaning of boards.
- Will work in any type of spray fluxer.
- Increased activity level.
- Conforms to IPC ANSI-J-STD-004, Type ORL0.

DESCRIPTION

Superior No. 420-S VOC-Free, No-Clean flux is a halide-free, rosin-free, no-residue flux specifically developed for spray fluxing in wave soldering applications for surface mount, mixed technology, and through-hole electronics assembly. **Superior No. 420-S** is a water-based, non-flammable formulation that eliminates the need for special storage requirements, while dramatically reducing VOC emissions from plants engaged in wave soldering.

PROCESS RECOMMENDATIONS

WAVE SOLDERING

Superior No. 420-S VOC-Free, No-Clean flux is formulated for spray fluxing application in a wave soldering system. The optimum topside PCB preheat temperature recommendation is 200-240°F/93-115°C. Too low a preheat setting is indicated by post-solder residues on PCBs that look like water stains.

The following items are critical when setting the conveyor speeds for VOC-Free fluxes:

- ➊ Conveyor speed and preheat settings should be adjusted to ensure complete water removal from the PCBs before contact is made with the solder wave.
- ➋ In most machines, a conveyor speed of 4-6 ft./min is acceptable, where the preheat section is a 4 ft. minimum. However, conveyor settings must be established by operators to meet the process needs of PCBs requiring special attention.

The following procedures are recommended for optimum performance.

- ➊ Make certain that the PCB surfaces are free of any oil, grease, or other impurities.
- ➋ Replace the flux daily unless it is in a sealed, self-contained system.
- ➌ Regularly clean the fluxing equipment.

Superior manufactures quality fluxes. Our business is solving problems.



SAFETY AND HANDLING PRECAUTIONS

Superior No. 420-S VOC-Free, No-Clean flux is a non-flammable, non-hazardous product. However, it is recommended that standard chemical safety practices be observed when handling this product. Avoid contact with eyes, skin, and mucous membranes. The use of rubber gloves, goggles and, or face shield is recommended. Use with adequate ventilation. Refer to the Material Safety Data Sheet (MSDS) for additional information. **Superior No. 420-S** VOC-Free, No-Clean flux has a two (2) year shelf life.

Superior No. 420-S VOC-Free, No-Clean flux should be stored in plastic containers away from heat. In the event the flux is exposed to temperatures below 0°C/32°F, the flux may freeze. Freezing will not degrade this product if these steps are followed:

- 1 Thaw flux until room temperature is reached.
- 2 Agitate flux to return to proper consistency.

PHYSICAL PROPERTIES

Specific Gravity	1.0075 ± 0.0075 @ 20-25°C/68-77°F
Pounds/Gallon	8.50 ± 0.20 @ 20-25°C/68-77°F
pH	2.40 ± 0.5
Acid Number	24.0 ± 6.0
Total Solids	2.0 ± 0.2
Flash Point	None
Silver Chromate Paper Test	Passes
*Copper Mirror Test	Passes
Free/Thaw Test	Passes

THIS PRODUCT IS RoHS COMPLIANT

* Modified IPC Test Method: Passes copper mirror test when same flux is formulated with isopropyl alcohol as the solids from water-based formulation are reconstituted with alcohol.

ELECTROMIGRATION TEST

I. CONDITIONS

Test Pattern:	IPC-B-25 test pattern, 0.0125 in. space and 0.0125 in. wide lines.
Environment:	85°C, 85% Relative Humidity
Bias Voltage:	100 Volts DC
Test Voltage:	100 Volts DC
Conditional Potential:	0
Initial Reading:	96 hours conditioning
Final Reading:	500 hours

II. AVERAGE TEST RESULTS

Boards	Initial Readings	Final Readings
Minimum Requirements:	1.0 X 108 Ohms	1.0 X 108 Ohms
Control	4.45 X 1011 Ohms	4.35 X 1011 Ohms
Pattern Face Up	8.17 X 1011 Ohms	4.49 X 1012 Ohms
Pattern Face Down	6.80 X 1011 Ohms	8.50 X 1012 Ohms

III. VISUAL EXAMINATION

No evidence of any electro-migration when viewed under 10X magnification.

The information contained herein is based on data considered to be accurate and is intended for use by persons having technical skills at their own discretion and risk. Since conditions of use are outside of Superior Flux & Mfg. Co.'s control, we cannot assume liability for results obtained or damage incurred due to misuse, nor can we assume customer liability.

Superior manufactures quality fluxes. Our business is solving problems.



**Superior Flux
& Mfg. Co.**

6615 Parkland Blvd. • Cleveland, OH 44139 • Phone: 440-349-3000 • Fax:
440-349-3003 www.superiorflux.com • e-mail: info@superiorflux.com